Lexan* SL 2030V Sheet



Description Lexan* SL2030V is a UV-stabilized, transparent, polycarbonate sheet. The grade is specifically developed for the eye protection industry. In addition to excellent optical performance, it offers outstanding impact resistance, good stiffness and strength and ease of processing. Typical applications are: motor helmet visors, industrial visors and goggles, sport goggles, police helmet visors and sunglasses.

Typical Property Values

Property	Test Method	Unit	Value ⁺⁾
Physical			
Density	ISO 1183	g/cm ³	1.20
Water absorption, 24 hours	ISO 62	%	0.15
equilibrium		%	0.35
Optical			
Light transmission	ASTM D 1003	%	89.5
Mechanical			
Tensile stress, yield	ISO 527	MPa	60
Tensile modulus	ISO 527	MPa	2300
Elongation, yield	ISO 527	%	7
Elongation, break	ISO 527	%	110
Flexural strength, yield	ISO 178	MPa	100
Flexural modulus	ISO 178	MPa	2500
Izod notched Impact, 20 °C	ISO 180-1A	KJ/m²	65
-30 °C		KJ/m²	10
Gardner impact, 20 °C	SABIC Method	J	>37
-20 °C		J	>37
Thermal			
Vicat Softening Temp., Rate B/120	ISO 306	°C	145
Mold shrinkage	ISO 527	%	0.5-0.7
HDT, 0.45 MPa	ISO 75 /Be	°C	138
Thermal expansion	ASTM D696	1/°C	7×10 ⁻⁵

These property values have been derived from Lexan* resin data for the material used to produce this sheet product.

¥) Typical values only. Variations within normal tolerances are possible for the various textures. * Trademarks of SABIC Innovative Plastics IP BV



SABIC Innovative Plastics™

Lexan* SL 2030V Sheet



Product Datasheet

Chemical Resistance

Lexan SL2030V sheet has sufficient resistance to most mineral oils, greases, aliphatic hydrocarbons and acids under low or moderate stress levels. In applications where it will come into contact with these or other aggressive chemicals, specific (application related) testing of the material is strongly recommended.

Product Availability

Texture	Gauges (mm)	Color
Polished/polished	0.75 1.00 1.50 2.00 3.00 4.00	several (transparent)



* Trademark of SABIC Innovative Plastics IP BV

Americas: SABIC Innovative Plastics Specialty Film & Sheet One Plastics Avenue Pittsfield, MA 01201 USA Tel. (1) (413) 448 5400 Fax. (1) (413) 448 7506 Toll free: 1-800 451 3147 Europe: SABIC Innovative Plastics Specialty Film & Sheet Plasticslaan 1 NL - 4612 PX Bergen op Zoom The Netherlands Tel. (31) (164) 292911 Fax. (31) (164) 293272

Pacific: SABIC Innovative Plastics Specialty Film & Sheet 1266 Nanjin Road (W) Plaza 66, 17th Floor 200040 Shanghai, China Tel. (86) 21 62881088 Fax. (86) 21 62880818

THE MATERIALS, PRODUCTS AND SERVICES OF SABIC INNOVATIVE PLASTICS HOLDING BV, ITS SUBSIDIARIES AND AFFILIATES ("SELLER"), ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH CAN BE FOUND AT http://www.sabic-ip.com AND ARE AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION OR RECOMMENDATION CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SELLER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SELLER'S PRODUCTS, SERVICES OR RECOMMENDATIONS. EXCEPT AS PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user is responsible for making its own determination as to the suitability of Seller's products, services or recommendations for the user's particular use through appropriate end-use testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. No statement by Seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of such product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC Innovative Plastics is a trademark of Sabic Holding Europe BV

* Trademark of SABIC Innovative Plastics IP B

www.sabic-ip.com